

## LABORATORY REPORT

Dated Reported: 10/10/2019  
Date Received: 25/09/2019

Report No: GCD/LR/1465/2019  
Report No: GCD/1465

To  
Wathnan Industries  
Qatar

Sample Submitted: Recycled Base Oil

Container Type: 1 X 500ml PB

Sample received from: Wathnan Industries

Seals on sample: Nil

Description on Label:  
Recycled Base Oil  
SN 350

The above sample was examined as detailed below and following results obtained.

TEST	METHOD	UNIT	RESULT
Density @ 15°C	ASTM D 1298	kg/l	<b>0.8603</b>
Flash Point	ASTM D 92	°C	<b>174</b>
Base No.	ASTM D 974	mg/KOH	<b>0.02</b>
Pour Point	ASTM D 97	°C	<b>-9</b>
Color	ASTM 1500	-	<b>&lt;4.5</b>
Viscosity @ 100°C	ASTM D 445	cST	<b>11.01</b>
Viscosity @ 40°C	ASTM D 445	cST	<b>61.76</b>
Viscosity Index	ASTM D 2270	-	<b>172</b>

Test conducted on	01-06/10/2019
Test method deviation:	None
Sampling method	N/A
Test conducted by Emp#:	696
Report prepared by Emp#:	696

The above test results are only applicable to the sample(s) referred above.



**NISHAN SAGAR**  
**CHIEF CHEMIST**

The Test Report shall not be reproduced (except in full) without the written approval of Geo-Chem Doha  
Samples retention period as per procedure QP/12, which shall be provided on request

*QA: F/48; Revision: 01; Revision Date: 15/01/2019.*

END OF REPORT

Page 1 of 1